

Data Sheet

FPO® PE Film 60

General

A paperlike blown film based on calcium carbonate (chalk) and polyethylene with a degree of filling above 50%.

It is an environmentally friendly material with a pleasant and natural feeling.

The film features excellent deadfold properties.

Applications

Wrap for butter and margarine.

Replacement of waxed paper.

Printing

High quality rotogravure, flexography, screen and offset printing. Treating 44 dyn/cm both sides as standard.

Material Properties

Property	Unit	Value	Instrument/Method	
Thickness	µm	60	Mitutoyo	
Grammage	g/m ²	76	Scale, 1dm ²	
Light Transm.	400 nm	%	4	Lambda 11 UV/VIS
Light Transm.	700 nm	%	41	Lambda 11 UV/VIS
Filler Content	%	51	ISO 3451-1	

Statement on Compliance to Food Contact Regulations according to EU Commission Directives are available.

Note: The stated values are typical data and are not specification of guarantee. RKW Sweden AB suggests that purchaser confirm product compatibility prior to use of this product. Stated values are believed to be accurate, but all information is presented without guarantee or responsibility on the part of RKW Sweden AB.
